



ISOLANTE ACRILICO MICRONIZZATO

MICRONIZED ACRYLIC INSULATOR

Description of product

Micronized Primer, mixture of acrylic resins in aqueous solution and high penetrating capacity.

Application Field

Primer for interior and exteriors.

Product characteristics

ISOLANTE ACRILICO MICRONIZZATO is composed of acrylic resins in aqueous solution. The very fine particles, 0,003 micron, give this special resin a higher penetrating capacity. Particularly suitable to consolidate friable and dusty surfaces, in order to support further spreadings of emulsion paints or wall varnishes. Excellent for cement, plaster, bricks, plasterboard and old hydro-paints. The colour shades can be personalized using the colour scheme of the Tintometric system Luxury&Lime.

Technical data	
Name	Isolante Acrilico Micronizzato
Composition	Acrylic resin in aqueous solution
Aspect	Liquid
Color	Milky White
Dilution	In water 100 - 300%
Quantity per layer	approx. 6 - 10 m2/kg
PH	9,5
VOC class	VOC 0g/l - wall paint and subcategory "L" max.value UE2010 30g/l
Specific weight	1 kg/litre
Packaging	1 - 5 - 10 lt packaging
Storage	Keep in dry place with temperture min.5° - 30°C max.
Notice	Protect the surfaces during the 12 hours after application

ISOLANTE ACRILICO MICRONIZZATO

Instructions for use

- Shake before use. Application with paintbrush, roller, sprayer
- Application of 1 or more coatings
- Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base
- ISOLANTE ACRILICO MICRONIZZATO must be diluted in water with range 1:3/1:4 and carefully stirred
- Spread one or more coats according to absorption of surface, using a long bristle paintbrush (wash paintbrush immediately after use)
- For porous surfaces use concentrated product
- Protect from rain. Verify that the insulator be completely consolidated
- Proceed with painting after at least 24 hours
- Temperature of application 10° - 35°C. Don't use on wet or metal surfaces

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.04.2004

BeriCalce ITALIA

Via Odorico da Pordenone, 18

36100 Vicenza - ITALY

Phone (+39) 0444 929102

Fax (+39) 0444 929102

Skype: bericalce

info@bericalce.com

bericalce.com