



ISOLANTE ANCORANTE BERICO

ANCHOR INSULATOR BERICO

Description of product

Granular anchor primer: in a dense solution to be applied by paintbrush or roller, acrylic base resin with granular micro-marble (300 micron).

Application Field

Micro-granular primer for interiors and exteriors.

Product characteristics

ISOLANTE ANCORANTE BERICO is an innovative primer, especially studied for surfaces that need a strong anchor primer. The product offers ideal conditions to grant a solid and strong anchorage for spatolati and marmorini on smooth and treated surfaces. ISOLANTE ANCORANTE BERICO is a dense product, once diluted the thixotropic remains and does not drain; the micro-grits remain homogeneously mixed in the paste to obtain an uniform application. The aspect is slightly rough and white colour. The colour shades can be personalized using the colour scheme of the Tintometric system Luxury&Lime.

Technical data	
Name	Isolante Ancorante Berico
Composition	Acrylic resins mixed with powders and marble micro-grits of 250 microns
Aspect	Dense Paste
Color	White
Dilution	In water 10 - 40%
Quantity per layer	approx. 4 - 6 m ² /kg
PH	9,5
VOC class	VOC 5g/l - wall paint and subcategory "L" max.value UE2010 30g/l
Specific weight	1,4 kg/litre
Packaging	5 - 15 lt packaging
Storage	Keep in dry place with temperture min.5° - 30°C max.
Notice	Protect the surfaces during the 12 hours after application

ISOLANTE ANCORANTE BERICO

Instructions for use

- Application of 1 coat
- Prepare the surface:
 - Old paintings must be well stick, clean and dry, any unsubstantial parts must be removed.
 - eliminate traces of oil or grease
 - level any irregularity of the base
 - consolidate and plaster any cracks or holes
- b) ISOLANTE ANCORANTE BERICO must be diluted in water and carefully stirred
 - apply 1 or more coats according to needs
 - for surfaces particularly porous apply a concentrated layer
 - protect from rain
 - verify that the product be completely consolidated
- c) Proceed with the second coat after at least 24 hours
 - temperature of application 10° - 35°C
 - do not apply on wet or metal surfaces

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.04.2004

BeriCalce ITALIA

Via Odorico da Pordenone, 18

36100 Vicenza - ITALY

Phone (+39) 0444 929102

Fax (+39) 0444 929102

Skype: bericalce

info@bericalce.com

bericalce.com